



# TYPICAL PROPERTIES

Reference Document No. TP-514

<b>Material Name:</b> CHEMRAZ® 514	<b>Rubber Classification:</b> FFKM	<b>Service Temperature Range:</b> -30°C to 220°C (-22°F to 428°F)	<b>Color:</b> WHITE
---------------------------------------	---------------------------------------	--	------------------------

DESCRIPTION	TYPICAL
<b>Original Properties</b>	
Specific Gravity (D297)	2.12
Hardness, Shore A, Points (D2240)	70
Tensile Strength, p.s.i. (D1414)	1460
Elongation, % (D1414)	190
Modulus @ 50% Elongation, p.s.i. (D1414)	300
Modulus @ 100% Elongation, p.s.i. (D1414)	680
<b>Compression Set @ 25% Deflection</b>	
70 Hrs. @ 400°F, In Air, % Of Original Deflection (D395)	25

**Note**

Unless otherwise noted, all tests performed on 214 O-Rings.

■ **Contact Us**

Greene, Tweed & Co.    Tel: +1.215.256.9521  
Kulpsville, PA, USA    Fax: +1.215.256.0189  
www.gtweed.com

*Statements and recommendations in this publication are based on our experience and knowledge of typical applications of this product and shall not constitute a guarantee of performance nor a modification or alteration of our standard warranty which shall be applicable to such products.*

