

Akron Rubber Development Laboratory, Inc.



TEST CERTIFICATE

This document certifies Chemraz[®] 566 FFKM

From

Greene, Tweed & Co.

PASSED

The requirements for resistance to Rapid Gas Decompression (RGD)

In accordance with Annex B, ISO 23936-2, 2011 Edition and NORSOK M-710, Rev.3

Test Gas	90% / 10% Molar Volume CH ₄ / CO ₂
Test Temperature	100°C (212°F)
Test Pressure	150 Bar (2175 psig)
Number of Cycles	8
Decompression Rate	20 Bar/Minute (290 psi / min)
Seal Size	ISO 3601-1-312 Class A O-ring, 5.33 mm CX (.210")

Prepared By:

David Nuss
 David Nuss
 Staff Engineer

Approved By:

John V. Meser
 John Meser
 Manager, ARDL Engineering




An A2LA Accredited Testing Laboratory — Certificate Numbers 255.01 & 255.02
 ISO 9001:2008 Registered

ISO 9001:2008
 Registered

*Certificate Numbers 255.01 & 255.02

Letters and reports are for the exclusive use of the clients to whom they are addressed and shall not be reproduced, except in full, without the written permission of Akron Rubber Development Laboratory, Inc. (ARDL). The information contained herein applies to the specific material, products or processes tested or evaluated. No warranty of any kind is herein construed or implied. The liability of ARDL, Inc. shall be limited to the amount of consideration paid for services. ARDL, Inc. is accredited by A2LA for the test methods listed on the attached scope.

ARDL verifies that Chemraz® 566 FFKM o-ring specimens, supplied by Greene, Tweed & Co., have been subjected to a multi-cycle RGD test, as detailed below:

RGD TEST COMMISSIONED BY		
Greene Tweed & Co.		
SEAL COMPOUND DETAILS		
Seal Manufacturer	Greene Tweed & Co.	
Supplied By	Greene Tweed & Co.	
Compound name/number/reference	Chemraz® 566	
Elastomer type to ASTM D1418	FFKM	
Lot/batch no.	1002611277	
Seal Type	O-ring	
Manufacturing method	Not disclosed	
Seal size (ISO 3601-1-312)	312	
CSD (nominal)	mm	5.33
Mean CSD	mm	
RGD TEST CONDITIONS		
Temperature	°C	100±2
Pressure	Bar	150 +10/-5
No. of cycles		8
Dwell between cycles	Hour	1
Decompression rate (average)	Bar/min	20
Gas type	Mol%	90/10 CH ₄ /CO ₂
SEAL HOUSING DETAILS		
Seal compression direction	Radial	
Groove ID	mm	15.54 -0.05
Groove OD	mm	24.61 +0.05
Groove Width	mm	5.97 +0.25
Squeeze (average)	%	14.5
Groove fill (area basis)	%	80 to 85
Number of seals tested		4
ISO TEST SEAL RATINGS		
SEAL REPLICATE	RATING	PASS/FAIL
1	0,0,0,0	PASS
2	0,0,0,0	PASS
3	0,0,0,0	PASS
4	1,0,0,0	PASS
OVERALL RATING	PASS	
GENERAL		
Test laboratory		ARDL, Inc.
Test date		7-15 May 2014
Test gas certified and available	YES/NO	YES
Transducer CALIBRATION AVAILABLE	YES/NO	YES
P/T log available	YES/NO	YES
TEST LABORATORY STAMP/SIGNATURE		

The results indicate the material is resistant to the RGD cycles specified herein. The Chemraz® 566 FFKM material **PASSED** the Rapid Gas Decompression testing per the full requirements of ISO 23936-2 and NORSOK M-710, Rev.3, under the stated conditions.