

Chemraz® 513

Universal Compound for Conventional Applications

Chemraz® 513 is recommended for a wide variety of semiconductor equipment dry processing applications where seal reliability with minimal contamination is required. The material offers excellent performance in static plasma, photolithography, and diffusion processes where temperatures do not exceed 410°F (210°C) and high-sealing loads are not used. The hardness of this material allows for some hardware finish inconsistency.


Typical Properties	
Physical Properties	Typical
Color	White
Polymer Type	Perfluoroelastomer
Specific Gravity	2.22
Hardness, Shore A*	80
Mechanical	
Tensile Strength, psi (kPa)	1600 (11032)
Elongation, %	165
Tensile Modulus, psi (kPa)	
Modulus @ 50% Elongation	540 (3723)
Modulus @ 100% Elongation	1050 (7239)
Compression Set, 70 Hours @ 204°C @ 25% Deflection, %	25
Thermal	
Service Temperature Range	-22°F to 410°F (-30°C to 210°C)

Unless otherwise indicated, all tests are performed on AS 568A (-214) o-rings.

Not to be used for specification purposes.

* Test performed on button samples.

Note: Color variations and dark spots that might be observed in Chemraz® parts are considered cosmetic and an inherent result of the polymer curing process. They are not foreign matter and not anticipated to adversely affect the performance of the part in service. Please contact a Greene Tweed applications engineer for additional information.



Features and Benefits

- Good plasma resistance and physical properties
- Minimal contamination
- Excellent performance history as “universal product”

Applications

- Door seals
- Slit valves
- Window seals
- Isolator valve seals
- Lid seals
- Gas inlet seals
- KF fitting seals

Recommended Process Applications

- Metalization (CVD, PVD, sputtering, evaporation)
- Deposition (CVD, PECVD, RPCVD, HDPCVD, APCVD, SACVD, DCVD)
- Dry plasma etch
- Remote plasma cleans
- Dry ashing
- Ion implant
- Implant anneal
- Rapid thermal processing (RTP)

Contact Us

Greene Tweed
Kulpsville, PA, USA

Tel: +1.215.256.9521
Fax: +1.215.256.0189

Statements and recommendations in this publication are based on our experience and knowledge of typical applications of this product and shall not constitute a guarantee of performance nor modify or alter our standard warranty applicable to such products.
© 2018, Greene Tweed all rights reserved. All trademarks are property of their respective owners.

08/18-GT DS-US-SC-168