

# Chemraz® 629

## Minimum Particulation and Maximum Plasma Resistance

Chemraz® 629 FFKM is specifically developed by Greene Tweed to meet the rigorous demands of aggressive plasma systems. Its unique formulation provides enhanced plasma resistance in oxygen and fluorine plasma processes, resulting in minimal contamination, less downtime, and higher wafer processing yields.


Chemraz® 629 is developed from an advanced polymer using fluoro-polymer nano-composite technology particles. Recommended for both static and dynamic dry wafer processing applications such as etch, remote plasma cleans, and deposition (CVD, HDPCVD) with challenging gland designs and reduced sealing loads, it remains stable at service temps to 500°F (260°C).

## Features and Benefits

- Exceptional plasma resistance in oxygen and fluorine environments
- Minimal particulation and surface degradation
- High purity, very low metallic ion content
- High elasticity allows conformance to hardware and easier seal installation

## Applications

- Endpoint windows
- Bell jar seals
- Valve seals
- KF fitting seals
- Window seals
- Isolator valve seals
- Lid seals
- Gas inlet seals
- Slit valve seals
- Chamber seals



## Recommended Process Applications

- Deposition (CVD, PECVD, RPCVD, HDPCVD, APCVD, SACVD, DCVD)
- Dry plasma etch
- Remote plasma cleans
- Dry ashing
- Oxidation (LPCVD)/diffusion
- Metalization (CVD, PVD, sputtering, evaporation)

*Note: Color variations and dark spots that might be observed in Chemraz® parts are considered cosmetic and an inherent result of the polymer curing process. They are not foreign matter and not anticipated to adversely affect the performance of the part in service. Please contact a Greene Tweed applications engineer for additional information.*

## Chemraz® 629 Typical Properties

Physical Properties	
Color	Translucent Ivory
Polymer Type	Perfluoroelastomer
Specific Gravity	2.07
Hardness, Shore A*	75
Mechanical	
Tensile Strength, psi (kPa)	2225 (15340)
Elongation, %	215
Tensile Modulus, psi (kPa)	
Modulus @ 50% Elongation	300 (2068)
Modulus @ 100% Elongation	610 (4206)
Compression Set: 70 Hours @ 204°C @ 25% Deflection, %	30
Thermal	
Service Temperature Range	-4°F to 500°F (-20°C to 260°C)

Not to be used for specification purposes. Unless otherwise indicated, all tests are performed on AS 568A (-214) o-rings.

\* Test performed on button samples.

## Greene Tweed

1684 South Broad Street, PO Box 1307 | Lansdale PA 19446 USA | Phone: (+1) (215) 256-9521 | [www.gtweed.com](http://www.gtweed.com)

Statements and recommendations in this publication are based on our experience and knowledge of typical applications of this product and shall not constitute a guarantee of performance nor modify or alter our standard warranty applicable to such products.

© 2022, Greene Tweed all rights reserved. All trademarks are property of their respective owners.

06/22-GT DS-US-SC-162