



EPDM 963 Sealing Solutions

Compound No./Material Name:	Rubber Classification	Service Temperature Range:	Color:
EPDM 963	(ASTM D1418): EPDM	-65°F to 300°F (-54°C to 149°C)	Black

Description (ASTM Standard)	Typical
Original Properties	
Specific Gravity (D792)	1.19
Hardness, Shore M, Points (D2240)	81
Tensile Strength @ Break, psi [MPa] (D1414)	2,375 [16.4]
Elongation, % (D1414)	175
Modulus @ 100% Elongation, psi [MPa] (D1414)	1,145 [7.9]

Note: Unless otherwise noted, all tests performed on on -214 o-rings.

Contact Us

Greene Tweed
Kulpsville, PA, USA

Tel: +1.215.256.9521
Fax: +1.215.256.0189

Statements and recommendations in this publication are based on our experience and knowledge of typical applications of this product and shall not constitute a guarantee of performance nor modify or alter our standard warranty applicable to such products.
© 2019, Greene Tweed all rights reserved. All trademarks are property of their respective owners.

06/19-GT 00-00-00-000