

# Fusion™ 735 Sealing Solutions

Compound No./Material Name:

Fusion™ 735

Rubber Classification:

(ASTM D1418): FKM

Service Temperature Range:

-20°F to 450°F (-29°C to 232°C)

Description (ASTM Standard)	Typical
<b>Original Properties</b>	
Hardness, Shore A, Points (D2240)	75
Tensile Strength @ Break, psi [MPa] (D1414)	2,200 [15.2]
Elongation, % (D1414)	190
Modulus @ 100% Elongation, psi [MPa] (D1414)	980 [6.8]

*Note: Unless otherwise noted, all tests performed on -214 o-rings.*

## Contact Us

Greene Tweed  
Kulpsville, PA, USA

Tel: +1.215.256.9521  
Fax: +1.215.256.0189

Statements and recommendations in this publication are based on our experience and knowledge of typical applications of this product and shall not constitute a guarantee of performance nor modify or alter our standard warranty applicable to such products.  
© 2019, Greene Tweed all rights reserved. All trademarks are property of their respective owners.

04/19-GT TPS-US-AS-014