



## Fusion™ 755 Sealing Solutions

Compound No./Material Name:	Rubber Classification:	Service Temperature Range:	Color:
FUSION™ 755	(ASTM D1418): FKM	-20°F TO 450°F (-29°C TO 232°C)	BLACK

Description (ASTM Standards)	Typical
Original Properties	
Specific Gravity (D297)	1.990
Hardness, Shore A, Points (D2240)	75
Tensile Strength, psi [MPa] (D412)	2050 [14.1]
Elongation, % (D412)	180
Modulus @ 100% Elongation, psi [MPa] (D412)	975 [6.7]

Note: Unless otherwise noted, all tests performed on ASTM slabs and buttons.

### Contact Us

Greene Tweed  
Kulpsville, PA, USA

Tel: +1.215.256.9521  
Fax: +1.215.256.0189

Statements and recommendations in this publication are based on our experience and knowledge of typical applications of this product and shall not constitute a guarantee of performance nor modify or alter our standard warranty applicable to such products.  
© 2018, Greene Tweed all rights reserved. All trademarks are property of their respective owners.

07/18-GT DS-US-EN-008