

Thermoplastic Anti-Extrusion Rings

Sealing Solutions for Demanding Environments



Thermoplastic Solutions

Greene Tweed recommends that back-up systems be used for pressures above 1,500 psi, dependent on temperature, extrusion gaps, and surfaces finish.

Anti-extrusion rings can be supplied in a wide variety of standard or special designs. Standard materials held in stock are listed on the right side of this page.

Arlon® (PEEK)

A high-strength, 482°F (250°C) thermoplastic capable of withstanding steam and the aggressive conditions found downhole, Arlon® resists virtually all organic and aqueous chemicals over a wide temperature range, with the exception of concentrated inorganic acids at high temperature.

Arlon® is highly wear resistant and tough while retaining its mechanical properties over a wide temperature range to 482°F (250°C). Greene Tweed supplies virgin grade Arlon® and grades reinforced with glass, carbon fiber, and TFE.

Greene Tweed has back-up systems working at up to 40,000 psi or more with its Greene Tweed seal configuration.

Re-enforced TFE

Chemically inert at elevated temperatures and pressures, reinforced TFE has outstanding resistance to nearly all oilfield environments. Temperatures from -450°F to 600°F (-268°C to 315°C) can be achieved; however, TFE has only fair resistance to deformation under load. Greene Tweed uses fillers such as graphite or glass fiber to improve TFE's resistance to cold flow.



Contact Us

Greene Tweed
Houston, TX, USA

Tel: +1.281.765.4500
Fax: +1.281.821.2696

Statements and recommendations in this publication are based on our experience and knowledge of typical applications of this product and shall not constitute a guarantee of performance nor modify or alter our standard warranty applicable to such products.
© 2018, Greene Tweed all rights reserved. All trademarks are property of their respective owners.

EN-DS050-US-08-18-2016