



TEST CERTIFICATE: APT-TC-190414-02

Standard: API 6A 21st Edition Annex F.1.13.5.2

Material: Arlon 1555

Status: Qualified

Issued To: Greene, Tweed & Company
1930 Rankin Rd., Houston, TX 77073
October 3, 2019

Qualification Statement: The Arlon 1555 compound is qualified to API 6A 21st Edition according to Annex F.1.13.5.2 immersion testing for material class FF/HH 10% H2S design validation procedures meeting Norsok M710 Rev 3 sour aging acceptance criteria.

Qualification Parameters	
6A Gas 35%	10% H2S / 80% CO2 / 10% CH4
6A Hydrocarbon 60%	Kerosene (Diesel #1)
6A Water 5%	Water
Exposure	To the hydrocarbon phase
Pressure	1000 ± 100 psi
Duration	160 hours
Temperature	428°F (220°C)

Acceptance Criteria	
Property	Criteria
Volume	+5 / -1 %
Tensile Strength	± 50%
Elongation at Break	± 50%
Modulus (Secant 1%)	± 50%
Visual Concerns	None

Prepared By: *Joshua Kennedy*
Joshua Kennedy
Staff Scientist

Approved By: *J. Buc Slay*
J. Buc Slay
CTO

