



TEST CERTIFICATE: APT-TC-190415-03

Standard: API 6A 21st Edition Annex F.1.13.5.2
Material: Avalon 89
Status: Qualified

Issued To: Greene, Tweed & Company
1930 Rankin Rd., Houston, TX 77073
October 3, 2019

Qualification Statement: The Avalon 89 compound is qualified to API 6A 21st Edition according to Annex F.1.13.5.2 immersion testing for material class FF/HH 10% H2S design validation procedures meeting Norsok M710 Rev 3 sour aging acceptance criteria.

Qualification Parameters		Acceptance Criteria	
6A Gas 35%	10% H2S / 80% CO2 / 10% CH4	Property	Criteria
6A Hydrocarbon 60%	Kerosene (Diesel #1)	Volume	+5 / -1 %
6A Water 5%	Water	Tensile Strength	± 50%
Exposure	To the hydrocarbon phase	Elongation at Break	± 50%
Pressure	1000 ± 100 psi	Modulus (Secant 1%)	± 50%
Duration	160 hours	Visual Concerns	None
Temperature	392°F (200°C)		

Prepared By: *Joshua Kennedy*
Joshua Kennedy
Staff Scientist

Approved By: *J. Buc Slay*
J. Buc Slay
CTO

