

Etch

Semiconductor Solutions

Chemraz®: The Preferred Choice for Semiconductor Sealing Solutions

Greene Tweed's broad range of Chemraz® formulations are used by some of the world's leading semiconductor fabs because of their superior performance and reliability.

Chemraz® sealing solutions provide customers with an increased MTBR (mean time between repair) to reduce downtime and maintenance costs.

A Full Range of Materials for Every Fab

Greene Tweed offers a full spectrum of materials to suit the needs of a variety of semiconductor fabs. Greene Tweed has sealing solutions for fabs that use the most advanced technology nodes in the most aggressive operating environments, as well as those requiring less-stringent particle process controls.

Superior Performance

- Minimal metallic ion content
- Exceptional plasma resistance
- Low particle generation
- High dimensional stability

Operational Benefits

- Superior reliability
- Enhanced repeatability
- Maximum system uptime
- Lower cost of ownership

Technology Node	Material	Compression Set @25% Deflection, %	Max Service Temperature
	Chemraz® XPE Superior O ₂ plasma resistance to protect components	70 hours @ 240°C 22%	280°C
	Chemraz® E38 Excellent O ₂ plasma resistance with low contamination	70 hours @ 240°C 21%	260°C
	Chemraz® 629 Excellent O ₂ plasma resistance with low contamination	70 hours @ 240°C 30%	260°C
	Chemraz® XCD Superior thermal resistance; carbon-loaded	70 hours @ 240°C 32%	300°C
	Fusion® 707 Minimal contamination in FPD processing	70 hours @ 240°C 24%	220°C
	Fusion® F10 High performance at a low cost of ownership	70 hours @ 240°C 27%	220°C
	Chemraz® 541 Broad chemical compatibility, temperature range, and shape versatility	70 hours @ 204°C 25%	230°C

Process	Typical Application Temperatures	Process Environments	Recommended Products
Ash/Strip	25 - 280°C	O ₂ , CF ₄ , CHF ₃ , SF ₆ , O ₂ , H ₂	Chemraz® 629, 656 Fusion® F10, 742
Dielectric (Oxide) EtchType	25 - 280°C	CF ₄ , C ₃ F ₃ , CHF ₃ , SF ₆ , O ₂ , H ₂	Chemraz® 657, E38, XPE, 629, 550, 656 Fusion® F10, 706, 742
Conductor (Poly/Metal) Etch	25 - 280°C	CF ₄ , CHF ₃ , HBr, BCl ₃ , CCl ₄ , Cl ₂	Chemraz® E38, E48, XPE, 629, 656 Fusion® F10, 706

Dynamic Applications	Static Applications
Door seals Valves	Chamber seals Lid seals Electrostatic chuck seals Gas inlet/outlet/mixing block seals Window seals Center rings

The Greene Tweed Advantage

Greene Tweed has been developing high-performance sealing solutions to withstand the extreme conditions in semi-conductor fabs since the 1980s, and has continually evolved to meet the increasingly demanding needs of the industry.

Greene Tweed leverages decades of engineering and applications expertise to design customized solutions, including material selection and hardware designs based on specific operating environments, such as acids, solvents, bases, and ultra-pure H₂O applications.

Greene Tweed

1684 South Broad Street, Lansdale, PA 19446 USA | Phone: (+1) (215) 256-9521

gtweed.com

Statements and recommendations in this publication are based on our experience and knowledge of typical applications of this product and shall not constitute a guarantee of performance nor modify or alter our standard warranty applicable to such products.

© 2026, Greene Tweed all rights reserved. All trademarks are property of their respective owners. 07/26-GT DS-US-SC-ETCH-26